

PRODUCT DATA SHEET F-LON® 7030 Series

F-LON® 7030 is an advanced **chemical resistant** coating.

F-LON® 7030 is a high purity fluoropolymer coating with added abrasion resistance based on a unique alternating, copolymer offering excellent capability.

F-LON® 7030 Series

Recommended Dry Film Thickness	0.2 to 1.5mm
Substrates	Most metallic substrates.
Pre-treatment	Degrease followed by sandblasting.
Application method	Hand spray or automatic spray line.
Curing schedule	270°C
Operating Temperature	-40 to +150°C
Colours available	Grey
Typical applications	Pharmaceutical, Fine Chemicals and Semi-conductor process plant demanding high purity and low vapour permeation.
Other properties	Chemical resistance Increased abrasion resistance over F-LON 6020 Corrosion resistance

This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon, Caxton Hill, Hertford, Herts, SG13 7NL