

PRODUCT DATA SHEET F-LON® 7220 Series

F-LON® 7220 is an advanced **chemical resistance** coating.

F-LON® 7220 is an excellent fluoropolymer coating and conforms to FDA regulations governing coatings for direct food contact application.

F-LON® 7220 Series

Recommended Dry Film Thickness	75-150
Substrates	Most metallic substrates.
Pre-treatment	Degrease followed by sandblasting.
Application method	Hand spray or automatic spray line.
Curing schedule	380°C
Operating Temperature	-195°C-260°C
Colours available	Sparkling
Typical applications	Heat seal platens, Chemical containers, vessels requiring good nonstick and chemical protection.
Other properties	Chemical resistance Abrasion resistance Corrosion resistance Hydrophobic Cryogenic stability FDA Approved

This product data sheet is based on the best information currently available and is offered to users in good faith but without offering or implying a warranty that such information is correct or has not been amended. Nor may it be assumed that patents, copyrights or design registrations concerning systems referred to herein may be ignored.

F-LON® is a registered trademark of Fluorocarbon, Caxton Hill, Hertford, Herts, SG13 7NL

Issue 1